

Supplemental Material

CO₂ Capture Behaviors of Amine-Modified Resorcinol-Based Carbon Aerogels Adsorbents

Wenjing Xie^{1,2}, Meiqing Yu¹, Rui Wang¹

¹ School of Environmental Science and Engineering, Shandong University, Jinan 250199, P.R. China.

² Hainan Research Academy of Environmental Sciences, Haikou 571126, P.R. China.

Contents

Table S1. CO₂ adsorption capacities and the amine utilization ratios of the activated carbon aerogels with different amine loadings at 75 °C.

Fig. S1. CO₂ adsorption breakthrough curves of PEI-loaded CA-K-1 with and without surfactants addition.

Table S1. CO₂ adsorption capacities and the amine utilization ratios of the activated carbon aerogels with different amine loadings at 75 °C.

Sample	Adsorption capacity (mmol CO ₂ /g-adsorbent)	Adsorption capacity (mmol CO ₂ /g-PEI)	the amine utilization ratio (%)
CA-K-1-PEI-50	1.67	3.14	26.91
CA-K-1-PEI-55	2.06	3.58	30.70
CA-K-1-PEI-60	2.03	3.25	27.86
CA-K-1-PEI-70	0.88	1.17	10.04




Fig. S1. CO₂ adsorption breakthrough curves of PEI-loaded CA-K-1 with and without surfactants addition.